

**PRODUCT DESCRIPTION**

A two component system consisting of polymers. Once fully cured, the system provides excellent protection from the effects of mechanical and chemical attack.

**INTENDED USES**

POLINTEK® Lining & Protection Regular Metal is an advance technology :

1. Fast cure (accelerate accordance to the working temperature).
2. Anti-corrosion and molecular degradation.
3. Ultraviolet resistance.
4. Zero water absorption.
5. Single coat application.
6. Compatible to all metal surfaces.
7. Adhere within wet or oily application.
8. Underwater application.
9. Food Grade

**PRACTICAL INFORMATION FOR POLINTEK® Lining & Protection Regular Metal**

<b>Color</b>	customize
<b>Gloss level</b>	N/A
<b>Volume Solid</b>	98 %
<b>Thickness</b>	1000 – 2000 microns
<b>Coverage Area</b>	1.3 kg for 1 m <sup>2</sup> area
<b>Method of Application</b>	Plural component airless spray, airless spray
<b>Drying Time</b>	

Over-coating Interval with self

<b>Temperature</b>	<b>Gelling</b>	<b>Touch Dry</b>	<b>Hard Dry</b>	<b>Minimum</b>	<b>Maximum</b>
25 <sup>0</sup> C (77 <sup>0</sup> F)	1 hour	2 hours	12 hours	2 hours	7 days
40 <sup>0</sup> C (104 <sup>0</sup> F)	0.5 hour	1 hour	6 hours	1.5 hours	5 days
Up to 350 <sup>0</sup> C (662 <sup>0</sup> F)	0.05 hour	0.1 hour	0.5 hours	0.1 hours	0.5 days

Note :

- Sufficient coating film strength has developed to permit the handling and movement of coated steelwork. A shore D hardness is a recommended guideline to indicate suitability for return to service.
- If the maximum over-coating interval is exceeded

**REGULATORY DATA**

See Material Safety Data Sheets (MSDS)