

## Lining & Protection Antifouling for Non Metal

### PRODUCT DESCRIPTION

A two component system consisting of polymers. Once fully cured, the system provides excellent protection from the effects of mechanical and chemical attack.

### INTENDED USES

POLINTEK® Lining & Protection Antifouling for Non Metal is an advance technology :

1. Fast cure (accelerate accordance to the working temperature).
2. Anti fouling.
3. Anti-corrosion and molecular degradation.
4. Ultraviolet resistance.
5. Zero water absorption.
6. Single coat application.
7. Compatible to all non metal surfaces.
8. Adhere within wet or oily application.
9. Hydrocarbon immersion resistance.
10. Underwater application.
11. Food Grade

### PRACTICAL INFORMATION FOR POLINTEK® Lining & Protection Antifouling for Non Metal

<b>Color</b>	customize
<b>Gloss level</b>	N/A
<b>Volume Solid</b>	98 %
<b>Thickness</b>	1000 – 2000 microns
<b>Coverage Area</b>	1.3 kg for 1 m <sup>2</sup> area
<b>Method of Application</b>	Plural component airless spray, airless spray
<b>Drying Time</b>	

Over-coating Interval with self

Temperature	Gelling	Touch Dry	Hard Dry	Minimum	Maximum
25 <sup>0</sup> C (77 <sup>0</sup> F)	1 hour	2 hours	12 hours	2 hours	7 days
40 <sup>0</sup> C (104 <sup>0</sup> F)	0.5 hour	1 hour	6 hours	1.5 hours	5 days
Up to 350 <sup>0</sup> C (662 <sup>0</sup> F)	0.05 hour	0.1 hour	0.5 hours	0.1 hours	0.5 days

Note :

- Sufficient coating film strength has developed to permit the handling and movement of coated steelwork. A shore D hardness is a recommended guideline to indicate suitability for return to service.
- If the maximum over-coating interval is exceeded

### REGULATORY DATA

See Material Safety Data Sheets (MSDS)